



3M™ Dyneon™

PTFE Granules TF 1645

Free-flowing PTFE for general moulding and ram extrusion

Features

- Meets ASTM D 4894 Type IV, Grade 2 classification
- Moulding powder with very good free-flowing properties
- Good mould filling behaviour
- Universal standard PTFE grade for general compression moulding and esp. for automatic moulding
- Good mechanical properties
- Low shrinkage

Typical applications

- Shaped parts
- Automatically and isostatically moulded articles
- Moulded cylinders
- Semi-finished articles

Typical properties

Powder properties

	Test Method	Unit	Value*
Bulk density	DIN EN ISO 60	g/l	840
Average particle size	ISO 13320	µm	450

Mechanical properties

Specific gravity	DIN EN ISO 12086	g/cm ³	2.15
Tensile strength (0,2 mm film)	DIN EN ISO 527-3	MPa	37
Elongation at break (0,2 mm film)	DIN EN ISO 527-3	%	400
Hardness Shore D	DIN EN ISO 868	-	56
Shrinkage	Internal Dyneon method	%	2,5
Tensile Modulus	DIN EN ISO 527	MPa	600
Deformation under load (15 MPa)	24 h similar to 100 h ASTM D 621	%	16 17
	permanent		10

Thermal properties

Thermal conductivity	DIN 52 612	W/m · K	0.22
Coefficient of linear expansion (parallel to moulding direction)	30-100 °C 30-200 °C 30-260 °C	DIN 53 752	K ⁻¹ 12 · 10 ⁻⁵ 14 · 10 ⁻⁵ 17 · 10 ⁻⁵
Flammability	UL 94		V-0

Electrical properties

Dielectric strength (0,2 mm film)	DIN EN ISO 12086	kV/mm	55
Volume resistivity	IEC 60093	Ω · cm	10 ¹⁸
Surface resistivity	IEC 60093	Ω	10 ¹⁷

*typical value

Processing

If transport or storage temperatures are too high, the material may agglomerate in its container. In such cases, it is advisable to store the material for 48 hours at below 23 °C and then sieve it (mesh size 4 mm) before filling the mould. To achieve optimum properties, compression moulding should be carried out within a temperature range of 23 °C to 26 °C at a pressure of 30 MPa .The sintering temperature should be in the range of 375 °C to 380 °C.

3M™ Dyneon™ PTFE Granules TF 1645



Supply Form

3M™ Dyneon™ PTFE Granules TF 1645 is supplied in moisture and dust tight plastic boxes with an inner polyethylene liner.

Quantity per box:	50 kg	25 kg
Order quantity per pallet	600 kg	300 kg

Storage and Material Handling

3M™ Dyneon™ PTFE Granules TF 1645 can be stored for a relatively long period of time. It should preferably be stored at a clean, dry place at a temperature of less than 30 °C. Before processing it is advisable to store the material in a sealed container for 24 hours in the production area. This is particularly important if ambient temperature is low; in such cases the material might be conditioned for up to 72 hours in the production area.

Safety/Toxicology

This is a PTFE material, so normal precautions observed with PTFE should be followed. Before processing these products, consult the Material Safety Data Sheet and follow all label directions and handling precautions. General handling/processing precautions include: (1) Process only in well-ventilated areas; (2) Do not smoke in areas contaminated with powder/residue from these products; (3) Avoid eye contact; (4) After handling these products wash any contacted skin with soap and water. (5) Avoid contact with hot fluoropolymer. Potential hazards, including evolution of toxic vapors, can exist if processing occurs under excessively high temperature conditions. Vapor extractor units should be installed above processing equipment. When cleaning processing equipment, do not burn off any of this product with an open flame or in a furnace.

Our Worldwide Commitment to Quality

Indicative of our commitment, most Dyneon design, development, production and service facilities have achieved global quality management certification. Production facilities have also received certification for their environmental management system. Please see the Dyneon website (www.dyneon.eu) for the most up-to-date certification details.

Important Notice

All information set forth herein is based on our present state of knowledge and is intended to provide general notes regarding products and their uses. It should not therefore be construed as a guarantee of specific properties of the products described or their suitability for a particular application. Because conditions of product use are outside Dyneon's control and vary widely, user must evaluate and determine whether a Dyneon product will be suitable for user's intended application before using it. The quality of our products is warranted under our General Terms and Conditions of Sale as now are or hereafter may be in force.

Technical information, test data, and advice provided by Dyneon personnel are based on information and tests we believe are reliable and are intended for persons with knowledge and technical skills sufficient to analyze test types and conditions, and to handle and use raw polymers and related compounding ingredients. No license under any Dyneon or third party intellectual rights is granted or implied by virtue of this information.

General recommendations on health and safety in processing, on work hygiene and on measures to be taken in the event of accident are detailed in our material safety data sheets.

You will find further notes on the safe handling of fluoropolymers in the brochure "Guide for the safe handling of Fluoropolymers Resins" by PlasticsEurope, Box 3, B-1160 Brussels, Tel. +32 (2) 676 17 32.

The present edition replaces all previous versions. Please make sure and inquire if in doubt whether you have the latest edition.

Dyneon Customer Service

Europe Phone: 00 800 396 366 27
Fax: 00 800 396 366 39

Italy Phone: 00 800 7 910 18
Fax: 00 800 7 810 19

USA Phone: +1 800 810 8499
Fax: +1 800 635 8061

Dyneon

Carl-Schurz-Strasse 1
D-41453 Neuss
Germany
Phone: +49 2131 14 2265
Fax: +49 2131 14 3857

Dyneon GmbH

Industrieparkstr. 1
D-84504 Burgkirchen
Germany
Phone: +49 8679 7 4709
Fax: +49 8679 7 5037

3M

3M Center
St. Paul, MN 55144
USA
Phone: +1 651 737 6501

Please contact us if you wish to know further addresses of any of our sales offices worldwide.

Web Site: www.dyneon.eu
Dyneon is a 3M company.

© Dyneon 2011
All Rights Reserved

3M and Dyneon are trademarks of 3M company
Used under license.

Printed in Germany
Issue: May 2011
98-0504-1890-8